

Method for controlled radical polymerization

The present invention relates to the field of polymers and of controlled polymerization. More particularly, a subject matter of the present invention is a novel controlled radical polymerization process which makes it possible to prepare polymers of high molar weight having a very low molar weight distribution index (polydispersity) over a relatively short polymerization time and with a very high conversion of monomer.

The development of polymers meeting the needs of new applications is one of the challenges of research. As the physical properties of a polymer are closely related to its macromolecular structure (architecture of the chains, polydispersity, and the like), controlling the synthesis of the polymer chains makes it possible to obtain polymers with well-defined properties. Currently, this approach is based on the use of conventional monomers and the control of the macromolecular structure is the main route for the development of novel polymers.

Living ionic polymerization makes it possible to synthesize polymers with well-defined macromolecular characteristics (molar weight, polydispersity index and architecture of the chains). However, very rigorous experimental conditions are required. Furthermore, this technique is generally applied to hydrophobic and nonpolar monomers, which greatly restricts its use.

Much greater use is made of radical polymerization as it is more flexible to employ: the presence of impurities is not totally unacceptable, the reaction can be carried out in an aqueous medium and a great many monomers can be used. However, it is difficult to control the macromolecular structure of the polymers formed, in particular that of block copolymers.

Controlled (or living) radical polymerization, combining the advantages of radical polymerization and the control of the macromolecular characteristics, is thus a cutting edge research subject.

5


Radical polymerization comprises three stages: initiation (creation of free radicals and reaction with the first monomer unit), propagation (successive additions of monomer units to the growing chain (macroradical)) and termination (halting of a chain) by coupling or disproportionation between two growing chains or by transfer of a proton to a growing chain.

15 The termination and transfer reactions affecting the (macro)radicals are responsible for the loss of control of the polymerization (formation of nonlinear polymers, high polydispersity). To obtain controlled radical polymerization, it is thus advisable to greatly reduce, indeed even to eliminate, these irreversible
20 termination and transfer reactions. The general principle consists in reversibly deactivating the active centers with the formation of dormant (unreactive) entities, in order to have a very low concentration of (macro)radicals in the medium
25 throughout the polymerization (de Barbeyrac J., March 2001, TechnoPol'der, No. 37, 6).

Two types of deactivation of (macro)radicals which make it possible to obtain controlled radical polymerization
30 have recently been developed:

- by reversible termination, either by coupling with a nitroxide (stable radical), generally referred to as the SFRP (Stable Free Radical Polymerization) process (Solomon D. et al., 1985, Chem. Abstr., 1985, 102, 221335g), or by coupling with a halogen atom, generally
35 referred to as the ATRP (Atom Transfer Radical Polymerization) process (Wang J.S. et al., 1995, Macromol., 28, 7901), and
- by reversible chain transfer, which process uses a

transfer agent including the following unit:



- 5 In the continuation of the description, the latter process will be referred to as "controlled radical polymerization process using an organosulfur reversible chain transfer agent".
- 10 An example of such a controlled radical polymerization process using an organosulfur reversible chain transfer agent is the RAFT (Reversible Addition Fragmentation Chain Transfer) process as disclosed in patent application WO 98/01478, where the chain transfer agent
- 15 is a dithioester. This RAFT process as disclosed in patent application WO 98/01478 is carried out at a uniform temperature and makes it possible to obtain polymers having different molar weights with variable polymerization times, polydispersity indexes and
- 20 conversions of monomer. With this process, when polymers are synthesized, in particular polymers with a high molar weight (greater than 100 000 g/mol), when the polymerization time is short, that is to say less than 8 hours, the conversion of monomer is low, that
- 25 is to say much less than 50%. In the reverse case, that is to say to obtain polymers with a high conversion of monomer, of greater than 80%, the polymerization time has to be high. The process disclosed in patent application WO 98/01478 thus has the disadvantage that
- 30 it does not make it possible to obtain polymers having a high molar weight in a short polymerization time and with a high conversion of monomer.

Patent application WO 99/31144 discloses a RAFT

35 polymerization process in which the transfer agent is chosen from xanthates and dithiocarbamates. The use of xanthates has the disadvantage that polymers with a

high molar weight can only be obtained with a very long polymerization time, of greater than 8 hours, a low conversion of monomer and a moderate polydispersity index much greater than 1.2. The use of
5 dithiocarbamates for the preparation of polymers having a high molar weight (of greater than 100 000 g/mol) makes it possible to improve the conversion of monomer and, to a lesser extent, the polydispersity index, without, however, reaching values of less than 1.2. To
10 achieve a polydispersity index of approximately 1.20, the polymerization time has to be greater than 8 hours.

The Applicant has now discovered, contrary to all expectation, that the control of the flux of initiator
15 radicals in the polymerization medium in a controlled radical polymerization process using an organosulfur reversible chain transfer agent makes it possible to prepare polymers having a high molar weight, at least equal to 100 000 g/mol, with a low polydispersity
20 index, in a short polymerization time, of less than 8 hours, and with a high conversion of monomer, of greater than 75%, these four criteria being obtained simultaneously. Furthermore, a linear growth of the molar weights with the conversion is obtained, which is
25 the essential criterion for a controlled polymerization.

Thus, a subject matter of the present invention is a process for controlled radical polymerization using an
30 organosulfur reversible chain transfer agent which consists in preparing polymers having a molar weight of greater than 100 000 g/mol, with a polydispersity index of less than 1.2 for molar weights of less than 200 000 g/mol and of less than 1.4 for molar weights of
35 greater than 200 000 g/mol, with a degree of conversion of monomer of greater than 75% and a polymerization time of less than 8 h, characterized by the control of the flux of initiator radicals in the polymerization medium.

Before describing the invention in more detail, certain terms employed in the description and the claims, in addition to those indicated above, are defined below.

5 The term "molar weight" is understood to mean, within the meaning of the invention, the number-average molar weight, M_n , of the polymer chains formed. In the present case, it is obtained after analysis of the samples by steric exclusion chromatography using two
10 detectors, a detector of refractometer type coupled to a light scattering device, which makes it possible to have access to absolute molar weight values (in contrast to the relative molar weights obtained when calibration with polymer standards is used). The light
15 scattering device is a miniDawn device (Wyatt Technology) and the molar weights are determined with Astra software (Wyatt Technology).

As indicated above, the polydispersity index is the
20 distribution index of the molar weights which is well known to a person skilled in the art. Thus, the polydispersity index is PI , with $PI = M_w/M_n$, M_n being as defined above and M_w being the weight-average molar weight of the polymer chains. In the present case, it
25 was also determined with Astra software.

When the molar weight of the polymer synthesized according to the process of the invention is between 100 000 and 200 000 g/mol, this index is absolutely
30 less than 1.2. When the molar weight is greater than 200 000 g/mol, the polydispersity index is absolutely less than 1.4.

The source of initiator radicals which is appropriate
35 for the purposes of the invention includes the compounds which provide free radicals which add to the monomers to produce propagating radicals. The propagating radicals are radical entities which have added one or more monomer units and which are capable

of adding additional monomer units.

The term "control of the flux of initiator radicals in the polymerization medium" is understood to mean a
5 choice of polymerization conditions which makes it possible to obtain a high flux of initiator radicals during the initiation period, so that the polymerization is carried out over a duration of a few minutes, preferably a duration of less than 30 minutes,
10 preferably less than 15 minutes, and then, after the initiation period, a lower flux of radicals, and this until the end of the polymerization.

If the source of radicals is an initiating agent, the
15 control of the flux of radicals is carried out via the rate of decomposition of said initiator, which is chosen to be high during the initiation period and as low as possible after the initiation period while being sufficient for the polymerization to continue until a
20 conversion of at least 75% over a period of time of at most 8 hours. For example, if the $[\text{organosulfur agent}]_0/[\text{initiator}]_0$ molar ratio is 3.3, with $[X]_0$ meaning the molar concentration of reactant X at the beginning of polymerization, conditions (temperature,
25 nature of the initiator) are chosen so that the rate constant for decomposition of the initiator, k_d , is greater than $1 \times 10^{-5} \text{ s}^{-1}$, preferably greater than $5 \times 10^{-5} \text{ s}^{-1}$, during the initiation period and such that the rate of decomposition of the initiator is as low as
30 possible after the initiation period, the value of k_d , however, remaining greater than $2 \times 10^{-7} \text{ s}^{-1}$, a nonzero residual concentration of initiator being retained until the end of the polymerization, in order for the polymerization to continue up to a conversion of at
35 least 75% over a period of time of at most 8 hours. For the $[\text{organosulfur agent}]_0/[\text{initiator}]_0$ molar ratios other than 3.3, a person skilled in the art will adjust (by the choice of the initiator and/or the choice of the temperature) the k_d value in order to obtain the

same flux of radicals (which can be calculated from k_d and from $[initiator]_0$).

When the source of the radicals is a mixture of
5 initiating agents or any source of radicals other than
initiating agent (for example, spontaneous production
from the monomer or else high energy radiation, such as
an electron beam, X rays or gamma rays), the
polymerization conditions are chosen so as to obtain a
10 flux of radicals equivalent to that obtained with an
initiating agent during and after the initiation
period.

The term "initiation period" is understood to mean, in
15 a controlled radical polymerization using an organo-
sulfur reversible chain transfer agent, the period
between the beginning of the polymerization and the end
of the initiation, the end of the initiation corres-
ponding to the complete consumption of the chain
20 transfer agent and being observed visually by a change
in coloration of the medium.

The process for radical polymerization controlled by
use of an organosulfur reversible chain transfer agent
25 at the basis of the invention is as defined above and
is widely known to a person skilled in the art. It may
be defined as bringing identical or different monomers
into contact in the presence of an organosulfur
reversible chain transfer agent and of a source of
30 initiator radicals.

Insofar as the monomers used are identical, the process
of the invention makes it possible to prepare polymers
of homopolymer type. In the contrary case, it makes it
35 possible to prepare polymers of copolymer type, such as
random copolymers, for example alternating copolymers,
and block copolymers, each block being either a
homopolymer or a random copolymer.

The monomers appropriate for the purposes of the invention are any ethylenically unsaturated monomer and can be chosen from the group consisting of styrene, substituted styrenes, substituted or unsubstituted alkyl (meth)acrylates, acrylonitrile, methacrylonitrile, acrylamide, methacrylamide, derivatives mono- and disubstituted on the nitrogen of the acrylamide and of the methacrylamide, isoprene, butadiene, ethylene, vinylacetate and their combinations.

10

The functionalized versions of these monomers are also suitable for the purposes of the invention.

The specific monomers and comonomers which can be used in the invention include methyl methacrylate, ethyl methacrylate, propyl methacrylate (all the isomers), butyl methacrylate (all the isomers), 2-ethylhexyl methacrylate, isobornyl methacrylate, methacrylic acid, benzyl methacrylate, phenyl methacrylate, methacrylonitrile, α -methylstyrene, methyl acrylate, ethyl acrylate, propyl acrylate (all the isomers), butyl acrylate (all the isomers), 2-ethylhexyl acrylate, isobornyl acrylate, acrylic acid, benzyl acrylate, phenyl acrylate, acrylonitrile, styrene, glycidyl methacrylate, 2-hydroxyethyl methacrylate, hydroxypropyl methacrylate (all the isomers), hydroxybutyl methacrylate (all the monomers), N,N-dimethylaminoethyl methacrylate, N,N-diethylaminoethyl methacrylate, triethylene glycol methacrylate, N-methacryloyloxy-succinimide, itaconic anhydride, itaconic acid, glycidyl acrylate, 2-hydroxyethyl acrylate, hydroxypropyl acrylate (all the isomers), hydroxybutyl acrylate (all the isomers), N,N-dimethylaminoethyl acrylate, N,N-diethylaminoethyl acrylate, triethylene glycol acrylate, N-acryloyloxysuccinimide, methacrylamide, N-methylacrylamide, N,N-dimethylacrylamide, N-(tert-butyl)methacrylamide, N-(n-butyl)methacrylamide, N-methylolmethacrylamide, N-ethylolmethacrylamide, N-(tert-butyl)acrylamide, N-octadecylacrylamide,


N-methylolacrylamide, N-ethylolacrylamide, N-acryloylmorpholine, vinylbenzoic acid (all the isomers), diethylaminostyrene (all the isomers), α -methylvinylbenzoic acid (all the isomers), diethylamino- α -methylstyrene (all the isomers), the acid or the sodium salt of p-vinylbenzenesulfonic acid, trimethoxysilylpropyl methacrylate, tributoxysilylpropyl methacrylate, the dimethoxymethylsilylpropyl methacrylate, diethoxymethylsilylpropyl methacrylate, dibutoxymethylsilylpropyl methacrylate, diisopropoxymethylsilylpropyl methacrylate, dimethoxysilylpropyl methacrylate, diethoxysilylpropyl methacrylate, dibutoxysilylpropyl methacrylate, diisopropoxysilylpropyl methacrylate, trimethoxysilylpropyl acrylate, tributoxysilylpropyl acrylate, dimethoxymethylsilylpropyl acrylate, diethoxymethylsilylpropyl acrylate, dibutoxymethylsilylpropyl acrylate, diisopropoxymethylsilylpropyl acrylate, dimethoxysilylpropyl acrylate, diethoxysilylpropyl acrylate, dibutoxysilylpropyl acrylate, diisopropoxysilylpropyl acrylate, maleic anhydride, N-phenylmaleimide, N-butylmaleimide, N-vinylpyrrolidone, butadiene, isoprene, chloroprene, ethylene, vinyl acetate and their combinations.

According to a specific embodiment of the invention, the monomer used in the process of the invention is a monomer derived from acrylamide or from acrylate, preferably N-acryloylmorpholine, N,N-dimethylacrylamide, N-(tert-butyl)acrylamide, N-octadecylacrylamide, n-butyl acrylate, t-butyl acrylate or N-acryloyloxysuccinimide and in particular N-acryloylmorpholine (NAM).

The amount of monomer to be added in the process of the invention is not limited by any one of the aspects of the process and will be easily determined by a person skilled in the art.

The organosulfur chain transfer agent is as defined


above, namely that it has the following unit:




These organosulfur chain transfer agents can be either
5 dithioesters, as disclosed in patent application
WO 98/01478, or xanthates, as disclosed in particular
in patent applications WO 98/58974, WO 99/31144,
WO 00/75207, WO 01/42312 and FR 00/07145, or
10 dithiocarbamates, as disclosed in particular in patent
applications WO 99/31144, WO 99/35177 and FR 00/07145,
or trithiocarbonates, as disclosed in particular in
patent applications WO 98/58974, WO 01/60792 and
WO 02/070571, or thioether thiones, as disclosed in
particular in patent application FR 99/07097, or
15 dithiocarbazates, as disclosed in particular in patent
applications US 6,380,335 and US 6,395,850, or
dithiophosphoric esters, as disclosed in particular in
patent application FR 2 812 293, or tetrathio-
phosphates, as disclosed in particular in patent
20 application FR 2 816 311.

The organosulfur chain transfer agent used for the
purposes of the invention can also be one of the
following novel dithioesters:


25 - 2,3-dimethylpropyl dithiobenzoate of formula:



- bis(3-methylbutyl) 2-(thiobenzoylthio)succinate of
formula:



- tert-nonyl dithiobenzoate of formula:



5 These novel compounds are obtained according to the procedure disclosed in patent application WO 01/92361 filed by the Applicant, apart from the fact that the sodium thiolate is suited to the final product desired.

10 According to one specific embodiment, the transfer agent is the dithioester tert-butyl dithiobenzoate.

The amount of transfer agent to be used is directly dependent on the molar weight desired for the polymer chains, according to the following equation, defined for controlled radical polymerizations using a reversible chain transfer agent (as disclosed, for example, in patent WO 98/01478):

20
$$M_n = \frac{[\text{monomer}]_0}{[\text{transfer agent}]_0} \times \text{conversion of monomer} \times M_{\text{mon}} + M_{\text{ta}}$$

where M_n is the number-average molar weight of the polymer chains, $[X]_0$ means the molar concentration of reactant X at the beginning of polymerization, and M_{mon} and M_{ta} are the weights of the monomer and transfer agent respectively.

The source of initiator radicals can be any method which generates free radicals and which produces free radicals capable of adding to monomer units to give propagating radicals.

5

The source of initiator radicals includes sources such as the thermally induced homolytic cleavage of one or more suitable compounds, such as peroxides, peroxyesters or azo compounds, spontaneous generation
10 from monomers, redox initiation systems, photochemical initiation systems and high energy radiation, such as electron beams, X rays or gamma rays. The initiation system is chosen so that, under the reaction conditions, there is not significant unfavorable
15 interaction between the initiator or radicals originating from the initiator and the transfer agent. The initiator must also have the solubility required in the reaction medium or the mixture of monomers.

20 Examples of initiator which can be used for the purposes of the invention comprise azo compounds and peroxides, such as 2,2'-azobis(2,4-dimethylvaleronitrile), 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-cyano-2-butane), 2,2'-azobis(methyl isobutyrate),
25 4,4'-azobis(4-cyanopentanoic acid), 4,4'-azobis(4-cyanopentan-1-ol), 1,1'-azobis(cyclohexanecarbonitrile), 2-(t-butylazo)-2-cyanopropane, 2,2'-azobis[2-methyl-N-(1,1)-bis(hydroxymethyl)-2-hydroxyethyl]-propionamide, 2,2'-azobis[2-methyl-N-(2-hydroxyethyl)]-
30 propionamide], 2,2'-azobis(N,N'-dimethyleneisobutyramidine) dihydrochloride, 2,2'-azobis(2-amidinopropane) dihydrochloride, 2,2'-azobis(N,N'-dimethyleneisobutyramidine), 2,2'-azobis(2-methyl-N-[1,1-bis(hydroxymethyl)-2-hydroxyethyl]propionamide), 2,2'-azobis(2-methyl-N-[1,1-bis(hydroxymethyl)ethyl]propionamide,
35 2,2'-azobis[2-methyl-N-(2-hydroxyethyl)propionamide, 2,2'-azobis(isobutyramide) dihydrate, 2,2'-azobis(2,2,4-trimethylpentane), 2,2'-azobis(2-methylpropane), 2,2'-azobis(2-(N-phenylamidino)propane) dihydro-

chloride, 2,2'-azobis(2-(N-(4-chlorophenyl)amidino)-
propane) dihydrochloride, 2,2'-azobis(2-(N-(4-hydroxy-
phenyl)amidino)propane) dihydrochloride, 2,2'-azobis-
(2-(N-benzylamidino)propane) dihydrochloride, 2,2'-azo-
5 bis(2-(N-allylamidino)propane) dihydrochloride,
2,2'-azobis(5-methyl-(N,N'-dimethyleneisobutyramidine))
dihydrochloride, 2,2'-azobis(2-(4,5,6,7-tetrahydro-1H-
1,3-diazepin-2-yl)propane) dihydrochloride, 2,2'-
azobis(2-(3,4,5,6-tetrahydropyrimidin-2-yl)propane)
10 dihydrochloride, 2,2'-azobis(2-(5-hydroxy-3,4,5,6-
tetrahydropyrimidin-2-yl)propane) dihydrochloride,
2,2'-azobis(2-(1-(2-hydroxyethyl)-2-imidazolin-2-
yl)propane) dihydrochloride, t-butyl peroxyacetate, t-
butyl peroxybenzoate, t-butyl peroxyoctoate, t-butyl
15 peroxyneodecanoate, t-butyl peroxyisobutyrate, t-amyl
peroxypivalate, t-butyl peroxypivalate, diisopropyl
peroxydicarbonate, dicyclohexyl peroxydicarbonate,
dicumyl peroxide, dibenzyl peroxide, dilauryl peroxide,
potassium peroxydisulfate, ammonium peroxydisulfate,
20 di(t-butyl) hyponitrite and dicumyl hyponitrite.

The initiator radicals can also be produced thermally
from the monomer (e.g., styrene), by the photochemical
route, from redox systems or by a combination of these
25 methods.

The photochemical initiation systems are chosen in
order to exhibit the required solubility in the
reaction medium or the mixture of monomers and have a
30 quantum yield appropriate for the production of
radicals under the polymerization conditions. Examples
of such systems include benzoin derivatives,
benzophenone, acylphosphine oxides and photoredox
systems.

35 The redox initiation systems are chosen in order to
exhibit the required solubility in the reaction medium
or the mixture of monomers and have a rate appropriate
for the production of radicals under the polymerization

conditions. Examples of such systems comprise the following combinations of oxidizing agents and reducing agents:

- oxidizing agents: potassium peroxydisulfate, hydrogen peroxide or t-butyl hydroperoxide,
- reducing agents: iron(II), titanium(III), potassium thiosulfite or potassium bisulfite.

Other appropriate initiation systems are described in the literature (see Moad and Solomon "The Chemistry of Free Radical Polymerization", Pergamon, London, 1995, pp. 53-95).

The amount of initiating agent to be added in the process of the invention is chosen so that the $[\text{transfer agent}]_0/[\text{initiator}]_0$ molar ratio is between 1 and 100, preferably between 2 and 50, preferably between 3 and 20.

As indicated above, the control of the flux of initiator radicals in the polymerization medium in a process for controlled radical polymerization using an organosulfur reversible chain transfer agent makes possible the production of polymers having molar weights of greater than 100 000 g/mol, with a low polydispersity index, in a polymerization time of less than 8 hours and with a degree of conversion of monomers of greater than 75%, which was not possible simultaneously with the processes of the prior art.

30

When the control of the flux of initiator radicals is achieved by the control of the decomposition of the initiating agent, this control can be implemented in two ways, namely using:

- a polymerization temperature gradient appropriately as a function of the polymerization stage under consideration, or
- a uniform polymerization temperature and an initiator having a high decomposition constant at the temperature

under consideration, that is to say greater than that of azobisisobutyronitrile (AIBN) at this temperature.

Thus, according to a specific embodiment, the control
5 of the flux of initiator radicals is achieved by the stages consisting in:

- i) maintaining a uniform polymerization temperature T_1 during the initiation period, and
- ii) continuing the polymerization, the polymerization
10 temperature being allowed to fall to the temperature T_2 ,

it being understood that T_1 and T_2 correspond to the following equations (1) and (2):

$$\begin{array}{ll} T_1 > T_2 & (1) \text{ and} \\ 15 \quad T_1 - T_2 \leq 50^\circ\text{C} & (2). \end{array}$$

The temperature T_1 is preferably a relatively high temperature for a polymerization temperature. Preferably, this temperature is between 60 and 95°C,
20 more preferably between 80 and 90°C.

The temperature T_2 is thus absolutely less than the temperature T_1 and is such that its difference from T_1 is not greater than 50°C. Preferably, this difference
25 is not less than 10°C.

When the difference between T_1 and T_2 is greater than 50°C, the 4 criteria are not met simultaneously. By way of example, if $T_1 = 95^\circ\text{C}$ and if $T_2 = 44^\circ\text{C}$, the
30 polymerization slows down considerably and it is not possible to achieve a high conversion in less than 8 hours.

According to one embodiment of the invention, T_2 is
35 between 40 and 75°C, more preferably between 50 and 70°C.

According to a preferred embodiment of the invention, T_1 is between 80 and 90°C, whereas T_2 is between 50 and

70°C. In a particularly preferred way, T_1 is equal to 80°C and T_2 is equal to 60°C.

5 The reduction in the temperature is carried out passively, for example by using a thermostatically-controlled bath, such as an oil bath, the temperature of which is regulated at T_1 during the initiation period and then at T_2 at the end of this period. In this case, the thermostatically-controlled device will
10 not operate as long as the temperature is greater than T_2 and will restart only where the temperature will be just below T_2 , in order to maintain a temperature T_2 .

15 This temperature gradient can also be implemented using a jacketed reactor connected to a thermostatically-controlled bath or using any other device for regulating the temperature.

20 When this temperature gradient is used, the nature of the initiator is not important and the initiators as defined above can be used. However, according to a specific embodiment, the initiator used is azobisisobutyronitrile (AIBN).

25 As indicated above, the control of the flux of initiator radicals can also be achieved by the use of an initiator which has the ability to decompose very rapidly.

30 Thus, according to another embodiment of the invention, the control of the flux of initiator radicals is achieved by adopting a uniform polymerization temperature and by using an initiating agent having a decomposition rate constant, k_d , which is greater than
35 that of AIBN at this same temperature.

Such initiating agents are widely known to a person skilled in the art and are, for example, 2,2'-azobis-(4-methoxy-2,4-dimethylvaleronitrile), 2,2'-azobis-

(2-cyclopropylpropionitrile), 2,2'-azobis(2,4-dimethylvaleronitrile), 2,2'-azobis[2-methyl-N-(2-hydroxyethyl)propionamide], 2,2'-azobis(N,N'-dimethyleneisobutyramidine) dihydrochloride, 2,2'-azobis(2-amidinopropane) dihydrochloride, 2,2'-azobis(N,N'-dimethyleneisobutyramidine), 2,2'-azobis(2-(N-phenylamidino)propane) dihydrochloride, 2,2'-azobis(2-(N-(4-chlorophenyl)amidino)propane) dihydrochloride, 2,2'-azobis(2-(N-(4-hydroxyphenyl)amidino)propane) dihydrochloride, 2,2'-azobis(2-(N-benzylamidino)propane) dihydrochloride, 2,2'-azobis(2-(N-allylamidino)propane) dihydrochloride, 2,2'-azobis(5-methyl-N,N'-dimethyleneisobutyramidine) dihydrochloride, 2,2'-azobis(2-(4,5,6,7-tetrahydro-1H-1,3-diazepin-2-yl)propane) dihydrochloride, 2,2'-azobis(2-(3,4,5,6-tetrahydropyrimidin-2-yl)propane) dihydrochloride, 2,2'-azobis(2-(5-hydroxy-3,4,5,6-tetrahydropyrimidin-2-yl)propane) dihydrochloride or 2,2'-azobis(2-(1-(2-hydroxyethyl)-2-imidazolin-2-yl)propane) dihydrochloride.

According to a specific embodiment, the initiating agent is the initiating agent 2,2'-azobis(2,4-dimethylvaleronitrile), known under the trade name (Wako) of V65.

In this embodiment, where a uniform polymerization temperature and a specific initiating agent are used, the polymerization temperature is, for example, 60°C with V65.

The process of the invention thus makes it possible to provide polymer chains having a high molar weight, of greater than 100 000 g/mol, with a very low polydispersity index, less than 1.2 when the molar weight is less than or equal to 200 000 g/mol and less than 1.4 when the molar weight is greater than 200 000 g/mol, with a high conversion of monomer, of greater than 75%, and in a short polymerization time,

of less than 8 hours, these four parameters being considered simultaneously.

5 The process of the invention makes it possible for the first time to prepare polymers of acrylamide or of its derivatives having a number-average molar weight of greater than or equal to 100 000 g/mol, it being understood that, when the molar weight is absolutely less than 200 000 g/mol, the PI is less than 1.2 and,
10 when the molar weight is greater than 200 000 g/mol, the PI is less than 1.4. These novel polymers, capable of being obtained by the process according to the invention, constitute another subject matter of the invention.

15 According to a specific embodiment, such a novel polymer is an N-acryloylmorpholine polymer.

20 The polymers obtained according to the process of the invention have applications in many fields and can make it possible in particular to improve the mechanical properties (strength, elasticity, adhesion) and the rheological properties (increase in the viscosity) of various formulations in the fields of adhesives,
25 paints, inks, and the like.

Finally, the polymers of the invention can be used as calibration standards for molar weights, particularly as regards polyacrylamide derivatives, for which there
30 do not currently exist standards for a molar weight of greater than 100 000 g/mol having a polydispersity index of less than 1.5.

The invention will be better understood with the help
35 of the following examples, given by way of illustration and without limitation, and with the help of figures 1 to 3, in which:

- figure 1 represents a graph showing the characteristics of conversion, molar weight and

polydispersity index of an N-acryloylmorpholine homopolymer obtained with the process of the invention using a temperature gradient,

5 - figure 2 represents a graph showing the characteristics of conversion, molar weight and polydispersity index of an N-acryloylmorpholine homopolymer obtained with the process of the invention using the initiator V65, and

10 - figure 3 represents a graph showing the characteristics of conversion, molar weight and polydispersity index of another N-acryloylmorpholine homopolymer obtained with the process of the invention using the initiator V65 in which the concentration of starting monomer has varied.

15

Example 1: Preparation of NAM homopolymers

1.1 General procedure

20 The N-acryloylmorpholine (NAM, sold by Polysciences Inc., reference 21192) is distilled before use in polymerization.

The dioxane (solvent) sold by SDS, reference 27,053-9)
25 is distilled over LiAlH_4 before use.

The azobisisobutyronitrile AIBN (polymerization initiator) (Fluka, reference 11630) is recrystallized from ethanol.

30

The azobis(dimethylvaleronitrile) (polymerization initiator) (Wako, reference V65) is recrystallized from ethanol.

35 The trioxane (internal reference for monitoring by ^1H NMR) (sold by Janssen-Chimica, reference 14.029.61) is used as is.

The transfer agent used is tert-butyl dithiobenzoate,

prepared according to the procedure disclosed in patent application WO 01/92361, that is to say as indicated in part 2.1 below, apart from the fact that 3-mercapto-2-butanol is replaced by sodium t-butylthiolate. The polymer chains formed using this transfer agent carry, at one of their ends, a dithioester functional group (which can be easily hydrolyzed to a thio functional group, for example by the action of a primary amine) and, at the other end, a t-butyl functional group.

1.2 Synthesis of the homopolymer A using a temperature gradient

The various reactants (monomer, tert-butyl dithiobenzoate, radical initiator AIBN, trioxane, dioxane) (see concentrations in table 1) are introduced into a reactor of Schlenk type at ambient temperature and the mixture is degassed by a sequence of freezing/vacuum/defrosting cycles, in order to remove any trace of oxygen, and then placed under nitrogen. The reaction mixture is brought to the desired temperature, 80°C, with stirring. After the change in color of the reaction medium from purple to orange-colored, characteristic of the complete consumption of the t-butyl dithiobenzoate (6 min), the set point of the thermostatically-controlled bath is fixed at 60°C. The temperature of the bath gradually decreases to this value in 35 min.

Samples are withdrawn regularly (with a hollow needle under nitrogen) and analyzed to determine the kinetics and the change in the molar weights with the conversion.

1.3 Synthesis of the homopolymers B and C using the initiator V65

The various reactants (monomer, tert-butyl dithiobenzoate, radical initiator V65, trioxane, dioxane) (see concentrations in table 1) are introduced

into a reactor of Schlenk type at ambient temperature and the mixture is degassed by a sequence of freezing/vacuum/defrosting cycles, in order to remove any trace of oxygen, and then placed under nitrogen.

5 The reaction mixture is brought to a temperature of 60°C with stirring and is maintained at this temperature throughout the duration of the polymerization.

10 Samples are withdrawn regularly (with a hollow needle under nitrogen) and analyzed to determine the kinetics and the change in the molar weights with the conversion.

1.4 Kinetic monitoring of the polymerization:

15

The kinetic monitoring of the consumption of the monomers is carried out by ^1H NMR (Nuclear Magnetic Resonance) on a Varian Unity Plus 500 MHz spectrometer.

20 The samples to be analyzed are prepared by mixing 300 μl of each withdrawn sample with 300 μl of deuterated solvent: CDCl_3 . The ^1H NMR analysis is carried out by irradiating the dioxane peak. This method exhibits the advantage of analyzing the reaction
25 medium without evaporating the synthesis solvent and thus makes it possible to avoid possible conversions of the products.

The decrease in the peaks relating to the vinyl protons
30 of the monomers is monitored as a function of the time with respect to an internal reference, trioxane. Trioxane has the distinguishing feature of exhibiting a ^1H NMR peak in the form of a strong thin singlet isolated from the vinyl protons of the monomer NAM (see
35 figure 1 of patent application WO 01/92361 as example of NMR spectrum).

The conversions of the monomer are obtained by:

$$C_{NAM} = 1 - \frac{\left(\frac{H_{NAM}}{H_{trioxane}} \right)_t}{\left(\frac{H_{NAM}}{H_{trioxane}} \right)_0}$$

with C_{NAM} : conversion of NAM,

H_{NAM} : integral relating to a proton of the NAM,

5 $H_{trioxane}$: integral relating to the six protons of
the trioxane.

1.5 Conditions for analysis of the molar weights

10 Mn is the number-average molar weight of the polymer
chains formed, M_{peak} corresponds to the molar weight of
the dominant population and PI is the polydispersity
index, reflecting the homogeneity in the weights of the
polymer chains (the closer PI is to 1, the more
15 homogeneous in weight are the polymer chains).

Conditions for the analyses by SEC in the aqueous phase
with a light scattering detector (LSD):

- Columns: Ultra Hydrogel 500 and 2000 (Waters),
- 20 - Pump: Waters 510,
- UV detector: Waters 484,
- Differential refractometric detector: Waters 410,
- Dynamic light scattering detector: MiniDawn three
angles, Wyatt Technologies,
- 25 - Eluent: Borate buffer, 0.05 M, pH = 9.3,
- Flow rate: 0.5 ml.min⁻¹.

The refractive index increment, (dn/dc) , of the NAM
homopolymer under these buffer conditions was
30 determined using an NFT ScanRef interferometer. A value
of 0.163 ml/g was obtained.

Operating conditions for the tests on
homopolymerization of NAM in the presence of t-butyl
35 dithiobenzoate according to the process of the

invention.

Table 1

| Homo-polymer | [NAM] (mol.l ⁻¹) | [NAM]/ [dithioester] | [Dithioester]/ [initiator] | Method of implementation Temperature and Initiating agent |
|--------------|---------------------------------|-------------------------|-------------------------------|--------------------------------------------------------------------|
| A | 3.75 | 709 | 3.3 | Temperature gradient AIBN |
| B | 3.75 | 709 | 3.3 | 60°C V65 |
| C | 3.75 | 3545 | 3.3 | 60°C V65 |

[X] means molar concentration of reactant X.

- 5 The monitoring of the polymerization characteristics is shown in the table below, the molar weights being obtained by SEC coupled to a light scattering detector (LSD).

Table 2


| Homo-polymer concerned | Polymeriz- ation time (h) | Conversion of monomer (%) | Mn (g/mol) | Mpeak (g/mol) | PI |
|---------------------------|---------------------------------|---------------------------------|---------------|------------------|------|
| A | | | | | |
| | 0.25 | 21.7 | 23 200 | 23 100 | 1.03 |
| | 0.42 | 32.1 | 36 200 | 33 500 | 1.02 |
| | 0.67 | 36.8 | 41 500 | 41 900 | 1.01 |
| | 1 | 41.1 | 45 300 | 46 700 | 1.02 |
| | 2 | 51.1 | 58 500 | 60 200 | 1.02 |
| | 5 | 67.7 | 84 600 | 87 700 | 1.05 |
| | 8 | 82.8 | 102 800 | 105 500 | 1.08 |
| B | | | | | |
| | 0.33 | 0.4 | | | |
| | 0.67 | 22.5 | 25 200 | 25 500 | 1.01 |
| | 0.92 | 36 | 39 100 | 39 300 | 1.01 |
| | 1.17 | 45.1 | 49 500 | 49 600 | 1.01 |
| | 1.5 | 55.1 | 60 400 | 61 000 | 1.04 |
| | 3 | 72.2 | 90 000 | 90 100 | 1.07 |
| | 6 | 90.5 | 106 500 | 107 000 | 1.10 |
| C | 0.67 | 15.2 | 74 400 | 86 600 | 1.08 |
| | 1 | 39.1 | 178 000 | 217 900 | 1.15 |
| | 1.5 | 59.9 | 242 300 | 324 500 | 1.30 |
| | 2 | 75.6 | 297 400 | 394 400 | 1.36 |

The results in the above table clearly demonstrate that the process of the invention makes it possible to prepare polymer chains having a high molar weight, of greater than 100 000 g/mol, with a very low polydispersity index, of less than 1.2 for weights of up to 200 000 g/mol and of less than 1.4 for weights of greater than 200 000 g/mol, with a high conversion of monomer, of greater than 75%, and in a short polymerization time not exceeding 8 hours, these four parameters being considered simultaneously.

In the three cases, a linear growth in the molar weights with the conversion is obtained, as represented in figures 1 to 3, figure 1 corresponding to the homopolymer A, figure 2 corresponding to the homopolymer B and figure 3 corresponding to the homopolymer C.

Example 2: Synthesis of novel transfer agents

2.1 Synthesis of 2,3-dimethylpropyl dithiobenzoate of formula:




150 ml of a 0.016 mol.l⁻¹ solution of thiobenzoylthioglycolic acid in diethyl ether are added, with vigorous stirring and at ambient temperature, to 100 ml of a 0.028 mol.l⁻¹ basic aqueous solution (0.1N NaOH) of 3-mercapto-2-butanol (Aldrich, reference 26,479-2) (1.2 equivalents) in a 500 ml round-bottomed flask. After reacting for 12 h, the ethereal phase is washed with two times 500 ml of a basic aqueous solution (1N NaOH) and then with 500 ml of a 10% aqueous solution of

NaCl. The 2,3-dimethylpropanol dithiobenzoate is purified by chromatography on silica gel (Kieselgel 60; eluent CH_2Cl_2); the purified product is obtained with a yield of greater than 90%.

5

2.2 Synthesis of bis(3-methylbutyl) 2-(thiobenzoylthio)succinate of formula:




10

The procedure shown in part 2.1 above was used again to prepare the title compound, apart from the fact that diisoamyl thiomalate (Acros, reference 26514) was used instead of 3-mercapto-2-butanol.

15

The purified product is obtained with a yield of 50%.

2.3 Synthesis of tert-nonyl dithiobenzoate of formula:



20

The procedure shown in part 2.1 above was used again to prepare the title compound, apart from the fact that tert-nonanethiol (Aldrich, reference 17,103-4) was used instead of 3-mercapto-2-butanol.

25

The crude product is obtained with a yield of 70%.